SCHÖNOX | RENOTEX® 3D SYSTEM










INSTALLATION OF THE SCHÖNOX RENOTEX® 3D SYSTEM

The Schönox Renotex® 3D System is designed to be installed on any type of suitable wood substrate. In new construction, no specific preparation is required. In renovation, you may leave acceptable, existing floor coverings in place if installed over sound wood substrates. Damaged areas, including large cracks, voids, or breakouts, must be addressed accordingly to prevent Schönox AP Rapid Plus self-leveler from flowing through the construction.

The sound insulating underlayment is cut to size and loose-laid, sheet-to-sheet, on the wood substrate. Take care to minimize any voids or joints to a width less than 1/8" between the sheets. The high density of the underlayment allows for walkability at any time. After the area has been properly covered with the sound-insulating underlayment, the gaps to the perimeter should be closed adhering the RS 50 foam tape to any vertical structure. The foam adds sound insulation, while the self-sticking lip glues down to the mineral wool to prevent the AP Rapid Plus from flowing underneath.

Always follow the directions of the floor covering manufacturer regarding specific substrate conditions before installing the covering. It is always recommended that the substrate be free of any debris before installation.



OX RS 50 TE SSCHONOX RS 50




RANGE OF APPLICATION

A sound-dampening, fire-rated subfloor solution for wood construction, such as specified in multi-family projects, apartment buildings, student housing or senior living facilities.

- 14 1 K 14 11	
Substrate	Any wooden substrate in a renovation or new construction
Priming	No priming required
Sound Insultion / Decoupling	1/2" mineral wool underlayer Vertically insulated by installing Schönox RS 50 Foam Tape to any vertical structures
Reinforcement	Schönox Renotex® 3D
Leveling	Schönox Renotex® 3D must be completely covered by pouring Schönox AP Rapid Plus at a minimum thickness of 1/2"
Compressive Strength (ASTM 109/mod- aire cure only)	Schönox AP Rapid Plus 6300 PSI after 28 days 3800 PSI after 1 day
Flexural Strength (ASTM C348)	Schönox AP Rapid Plus + Schönox Renotex® 3D approximately 2,000 PSI after 28 days
IIC / STC / AIIC (ASTM E989-06 / ASTM 2179)	Exceeds IIC 50 / STC 50
UL Classification	UL FIRE RESISTANCE DIRECTORY: R38619 Included design modifications: L502, L503, L504, L505, L506, L507, L508, L509, L510, L511, L512, L513, L514, L515, L516, L517, L518, L519, L520, L522, L523, L524, L525, L526, L527, L528, L529, L530, L532, L533, L534, L535, L536, L537, L538, L539, L540, L541, L542, L543, L545, L546, L547, L549, L551, L552, L556, L557, L558, L560, L562, L563, L564, L565, L569, L570, L573, L574, L576, L577, L579, L581, L583, L585, L588, L589, L590, L592, L593, M500, M502, M503, M504, M505, M506, M507, M508, M510, M513, M514, M517, M18, M519
Fire Rating (ASTM E84)	Schönox AP Rapid Plus UL-classified in accordance with ASTM E84 (ANSI/UL 723): Flame Spread 0; Smoke Development 0


For more information, refer to the product technical data sheets.

AP RAPID PLUS DRYING SPEED



up to 3" with the Renotex® 3D System. Consult with your Schönox representative for more information.

AP RAPID PLUS FLEXURAL / COMPRESSIVE STRENGTH



Installation of floor covering

CHÖNOX RS 50

After the leveling compound is thoroughly dry, any type of flexible floor covering, wood floor, or ceramic tile may be installed on top following the referring product data sheet.



Installing of the insulation layer and Schönox RS 50

The insulation is loose-laid to the existing wood substrate, leaving a gap of approx. 1/8" to the perimeters. Schönox RS 50 foam tape decouples the insulation layer from any vertical structure.



Installing Schönox Renotex® 3D

The fabric is cut to shape using electrical scissors. The fabric is flattened lengthwise to overlap approximately 2". Adhere ends of Renotex® 3D along walls using double-sided tape, when necessary, to eliminate any possible curl.



Installing Schönox AP Rapid Plus

Schönox AP Rapid Plus is installed completely covering Schönox Renotex® 3D by using barrel mixer or pump and simply walking over the fabric. The system cures overnight to a completely decoupled, floating, and self-bearing system.

SCHÖNOX RENOTEX® 3D PRODUCT DATA

MATERIAL

- · Front Glass fiber
- · Back Glass fiber
- · Chain binding Textured polyester
- · Pile warp Polyethylene

ROVING PER SOUARE METER FRONT AND BACK

- 0° 79°
- 90° 109°

MESH SIZE FRONT AND BACK

- 0° 10 mm / .39"
- 90° 7 mm / .28"

ROLLS PER PALLET

• 6

WEIGHT PER ROLL

• 73 lbs.

PALLET WEIGHT

485 lbs.

ROLL DIMENSIONS

- 2m x 25m
- 78.74" x 984.25"
- · 6.56' x 82.02'

COVERAGE PER ROLL

· Approx. 540 sq. ft.

AP RAPID PLUS PRODUCT DATA

PRODUCT CHARACTERISTICS

- · For interior use only
- · Designed for fast-track installations over critical substrates
- · Dust-reduced properties
- · Self-leveling
- Suitable on underfloor heating systems
- · Very low shrinkage
- Pumpable
- · Suitable for castor wheel loadings
- · Layer thicknesses above 1/8" up to 3"

ABOUT SCHÖNOX AP RAPID PLUS

Schönox AP Rapid Plus is suitable for filling, smoothing, and leveling of substrates under:

- Flexible coverings
- · Wood floor, layer thickness above 1/8" Suitable on:
- · Concrete and cement substrates
- Gypsum substrates
- · Old floorings, such as ceramic tiles, terrazzo, sheet vinyl, rubber, and resilient floor coverings
- · Old, water-resistant adhesive residues
- · OSB board and plywood
- · In combination with decoupled Renotex® 3D System installation

MIXING RATIO

- Mix each 55lb. bag with 4.2 liters / 4.5 quarts of water
- · To extend AP Rapid Plus, we recommend mixing with dry, clean aggregate at a layer thickness above 2". Type and amount of aggregate used will affect product performance. We recommend performing tests before use on a larger scale.
- · Do not overwater! Foam while mixing or settling of the sand aggregate while placing, indicates overwatering.

TECHNICAL DATA

- Pot life: approx. 30 minutes at 68°F
- · Ready for foot traffic: approx. 2-3 hours
- · Ready for covering:
- after 16 hours at 1/2" thickness
- after 48 hours at 2" thickness
- Working temperature: 41°F 90°F
- Coverage per unit: approx. 14 sq. ft. at 1/2"
- · Compressive strength (ASTM C109):
 - 6300 PSI after 28 days
- 3800 PSI after 1 day

LEED V4.1 ID+C, BD+C

Contributes to LEED v4.1 certification of projects in these categories:

- EQc2 3 points Low-Emitting Materials
- MRc1 up to 2 points Life-Cycle Impact Reduction
- MRc2 1 point Environmental **Product Declaration**
- MRc3 1 point Sourcing of Raw Materials
- MRc4 1 point Material Ingredients

The Schönox Renotex® 3D System, in combination with Schönox AP Rapid Plus, is UL Classified.











Refer to Technical Data Sheets for additional, current information. Available on the Schönox app and at hpsubfloors.com.







